

DESCRIPTION

Total thickness	EN 428	mm	3.30
Thickness of wearlayer	EN 429	mm	1
Weight	EN 430	g/m ²	3320
Width of sheet	EN 426	cm	100
Length of sheet	EN 426	lm	22





CLASSIFICATION

Norm / Product specification	-	-	EN 651
European classification	EN 685	class	34 - 42
Fire rating	EN 13 501-1	class	C _{fl} -s1
Static electrical propensity	EN 1815	kV	
Slip resistance wet : ramp test with oil	DIN 51 130	class	

PERFORMANCE

Wear resistance	EN 660.2	mm	
Wear group	EN 651	-	T
Dimensional stability	EN 434	%	≤ 0.4
Residual indentation (exigency)	EN 433	mm	0.20
Residual indentation (measure)	-	mm	
Impact sound insulation	EN ISO 717-2	dB	17
Thermal conductivity	EN 12 524	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	-	Bonne
Anti-bacterial and fungicidal treatment	-	-	Sanosol®
Surface treatment	-	-	

CE MARKING

	EN 14041	-	  
		-	